


Fabreeka® Bearing Pads



Fabreeka pads are the original “fabric reinforced” bearing pad used in industry since 1918. The multiple laminations of rubber and fabric allow for large loading with minimal creep and virtually no shape factor associated with unreinforced bearing pad materials.



Fabreeka pads were first used as a bridge bearing in 1936 and are commonly used as a structural bearing element accommodating surface irregularity and rotations between load bearing faces. Fabreeka material is also used for vibration and shock applications.

Features and Attributes

- Distributes load between two structural elements evenly
- Accommodates non-parallel, load bearing surfaces
- Allows for rotations up to 0.02 radians under high pressure
- Ultimate compressive strength of 20,000 psi
- Meets AASHTO 18.4.9.1, MIL-C-882 and most state DOT specifications
- Provides vibration and shock isolation in structural applications


Physical Properties

<u>PROPERTY</u>	<u>TEST</u>	<u>SPECIFICATION</u>
<i>Hardness:</i> <i>Shore “A”</i>	ASTM D2240	90±5
<i>Tensile Strength:</i>	ASTM D412	5,500 psi (min)
<i>Ultimate Elongation:</i>	ASTM D412	17% (max)
<i>Compressive Strength:</i>		10,000 psi (min)
<i>Modulus of Elasticity:</i>		23,000 psi (max)
<i>Environmental:</i>	MIL-E-5272	Pass

Specification for Fabreeka® Bearing Pads

The bearing pads shall be manufactured of all new (unused) materials and composed of multiple layers of prestressed 50/50 cotton-polyester blend duck, 8.1 ounce per net square yard, duck warp count 50 ± 1 threads per inch and filling count 40 ± 2 threads per inch, impregnated and bound with a high quality, oil-impervious nitrile rubber compound, containing rot and mildew inhibitors and anti-oxidants, compounded into resilient pads of uniform thickness. The pads shall withstand compressive loads perpendicular to the plane of laminations of not less than 10,000 psi before breakdown.


Fabreeka Pad Static Deflection



Additional Products for Building & Construction



SA-47 Bearing Pads



PTFE Bearing Pads



Structural Expansion Bearings



Flexible Drain Trough

World Headquarters
Fabreeka International, Inc.
PO Box 210
1023 Turnpike Street
Stoughton, MA 02072
Tel: (800) 322-7352
Tel: (781) 341-3655
Fax: (781) 341-3983
E-mail: info@fabreeka.com
www.fabreeka.com

Germany
Fabreeka GmbH Deutschland
Hessenring 13
D-64572 Büttelborn
Tel: 49 - (0)6152-9597-0
Fax: 49 - (0)6152-9597-40
E-mail: info@fabreeka.de
www.fabreeka.de

England
ACE Fabreeka UK
Unit 404 Easter Park
Haydock Lane
Haydock WA11 9TH
Tel: 44 - (0)1942 727440
Fax: 44 - (0)1942 717273
E-mail: info@ace-fabreeka.com
www.fabreeka.co.uk

Taiwan
Fabreeka International, Inc.
PO Box 1246
Tainan 70499
Taiwan
Tel: 886-935 273732
E-mail: info@fabreeka.tw
www.fabreeka.com.cn